

Subsurface Aluminum Label & Tag Durability

| CHARACTERISTIC | TEST CONDITION | EFFECT |
|----------------------------------|---|----------------|
| Exterior Exposure | Exceeds 400 hour Weatherometer. Test GG-P-455B. Estimated equivalent of 20 years outdoor exposure | No effect |
| Abrasion Resistance | Taber Abraser with CS17 wheel, 100 gm. load for 7,000 cycles. | Slight dulling |
| Temperature Resistance | 1,000 degrees F | No effect |
| Salt Spray | 5% at 95 degrees F for 700 hr. | No corrosion |
| Chemical Resistance | | |
| MIL-S-3136 111 Hydrocarbon Fluid | 1 hr. immersion | No effect |
| MIL-L-5161C Jet Fuel | 1 hr. immersion | No effect |
| JP-4 fuel | 72 hr. immersion | No effect |
| Kerosene | 12 hr. immersion | No effect |
| Hydraulic Fluid | 24 hr. immersion to boiling point | No effect |
| Methyl Ethyl Ketone | 24 hr. immersion | No effect |
| Ethyl Acetate | 24 hr. immersion | No effect |
| Xyol | 72 hr. immersion | No effect |
| Heptane | 72 hr. immersion | No effect |
| Ethyl Alcohol | 72 hr. immersion | No effect |
| Ferric Chloride | 10% solution, 16 hr. immersion | No effect |
| Ammonium Hydroxide | 10% solution, 16 hr. immersion | Slight dulling |
| MIL-P-21563 soap solution | 16 hr. immersion | No effect |
| Sulfuric Acid | 10% solution, 24 hr. immersion | No effect |
| Phosphoric Acid | 1% solution, 12 hr. immersion | No effect |
| Nitric Acid | 3% solution, 72 hr. immersion | No effect |
| Trisodium Phosphate | 1% solution, 40 hr. immersion | No effect |
| MIL-C-25179 AIN in heptane | 25% solution, 1 min. immersion | No effect |

800.382.2323 (toll free)
858.549.9828

858.549.8708
Mail@ExpressCorp.com

9155 Trade Place, San Diego, CA 92126 | ExpressCorp.com

ISO 9001:2008 Certified - ITAR Registered

Member: Automatic Identification Manufacturers Association

Member: AIM UID Supplier Alliance

Member: National Assn. of Graphic Identification Product Manufacturers

Member: Specialty Graphic Imaging Association



EXPRESS

IDENTIFICATION MADE SIMPLE