Ceramic Tag Durability

| CHARACTERISTIC | TEST CONDITION | EFFECT |
|----------------------------|--|--------------|
| Exterior Exposure | Simulated outdoor exposure testing indicates pre- dicted outdoor service life in excess of 100 years. | No effect |
| Surface Hardness | 5.0 on Moh's scale | |
| Abrasion Test | 500 cycles with CS-17 calibrase wheels with 100g load | No effect |
| Tensile Strength | Where mechanical stress places ceramic coating in tension a pattern of fine cracks, perpendicular to tensile stress will form. Steel core has strength of 44 KSI tensile. Where tag may be prone to bend, tensions capable of causing cracking of ceramic can occur. Use of heavier core can eliminate potential for bending | |
| Impact Test | 70g steel ball dropped from 1 meter, impacting tag surface perpendicular to descent of ball. | No effect |
| Temperature Resistance | 1,200 degrees F for 30 minutes | No effect |
| Salt Spray | 5% at 95 degrees F for 700 hr. | No corrosion |
| Chemical Resistance: | Resistant to most acids except hydrofluoric or con- centrated phosphorics. Resistant to most caustics except at elevated temperatures | |
| Hydrochloric Acid | 72 hr. immersion | No effect |
| Nitric Acid | 72 hr. immersion | No effect |
| Sulfuric Acid | 72 hr. immersion | No effect |
| Sodium Hydroxide | 50% solution, 72 hr. immersion | No effect |
| MIL-L-5161C Jet Fuel | 1 hr. immersion | No effect |
| JP-4 fuel | 72 hr. immersion | No effect |
| Kerosene | 12 hr. immersion | No effect |
| Hydraulic Fluid | 24 hr. immersion at boiling point | No effect |
| Methyl Ethyl Ketone | 24 hr. immersion | No effect |
| Ethyl Acetate | 24 hr. immersion | No effect |
| Ferric Chloride | 10% solution, 16 hr. immersion | No effect |
| MIL-P-21563 soap solution | 16 hr. immersion | No effect |
| MIL-C-25179 AIN in heptane | 25% solution, 1 min. immersion | No effect |

Technical data is provided for comparison purposes only. This data has been compiled from sources we believe to be accurate but cannot guarantee. Variable combinations of chemicals, temperature, pressures and chemical concentrations may produce varied results. Customer testing is recommended to determine actual suitability in any specific environment.

800.382.2323 (toll free)
858.549.9828

♣ 858.549.8708➡ Mail@ExpressCorp.com

9155 Trade Place, San Diego, CA 92126 | ExpressCorp.com

ISO 9001:2008 Certified - ITAR Registered Member: Automatic Identification Manufacturers Association Member: AIM UID Supplier Alliance Member: National Assn. of Graphic Identification Product Manufacturers Member: Specialty Graphic Imaging Association



Z.90039.1